

## BOQUILLAS PARA CORTAR CON ACETILENO

ESPESOR DEL METAL	TAMAÑO DE LA	PRESION EN		CONSUMO		VELOCIDAD DE CORTE	ANCHO DE LA RANURA	BROCAS LIMPIADORAS	
		OXIGENO	ACETILENO	OXIGENO	ACETILENO			ORIFICIO DE CORTE	ORIFICIO DE PRECALENT.
mm		kg/cm <sup>2</sup>	kg/cm <sup>2</sup>	m <sup>3</sup> /h	m <sup>3</sup> /h	cm/min	mm		
6.35	0	2.1	0.28	1.34	0.019	55.9	1.39	62	74
9.5	0	2.5	0.28	1.62	0.019	50.8	1.39	62	74
12.7	1	2.5	0.28	2.43	0.026	48.2	2.03	56	71
15.9	1	2.8	0.28	2.71	0.026	43.1	2.03	56	71
19	2	2.5	0.28	3.31	0.029	40.6	2.41	54	70
25.4	2	2.9	0.28	3.59	0.029	35.5	2.41	54	70
31.8	2	3.6	0.28	4.16	0.029	33	2.41	54	70
38.1	3	3	0.35	5.2	0.033	30.4	2.54	51	68
50.8	3	3.3	0.35	5.49	0.033	25.4	2.54	51	68
63.5	4	2.7	0.35	7.21	0.036	22.8	3.17	45	62
76.2	4	3.1	0.35	7.92	0.036	20.3	3.17	45	62
101.6	4	3.8	0.35	9.37	0.039	17.7	3.17	45	62
127	5	3.9	0.42	12.71	0.071	17.7	3.81	41	60
152.5	5	4.7	0.42	14.55	0.071	15.2	3.81	41	60
203.5	5	5.5	0.42	16.41	0.073	13.9	3.81	41	60
254	6	5.8	0.42	22.13	0.079	12.7	5.15	32	60
305	6	8.8	0.42	28.5	0.079	11.4	5.84	32	60